



CEWELD SG CrMo1 Tig

TYPE Copper coated welding wire for welding creep and hydrogen-resistant steels

ANWENDUNGEN High pressure boiler steels, offshore, repair, construction, pipelines, tubing etc.

EIGENSCHAFTEN Extreme easy to weld with excellent welding properties. Suitable to offer creep resistance for working temperatures up to 550° Celsius.

KLASSIFIKATION

AWS	A 5.28: ER 80S-G
EN ISO	21952-A: W CrMo1Si
W.Nr.	1.7339
F-nr	6
FM	3

GEEIGNET FÜR **Typ 1Cr0,5Mo, ISO 15608: ~5,1**
 1.7335, 1.7262, 1.7728, 1.7218, 1.7225, 1.7258, 1.7354, 1.7357, 1.7205, 1.7218, 1.7225, 1.7228, 1.7254, 1.7262, 1.7335, 1.7337, 1.7350, 1.7354, 1.7357, 13CrMoV42, 13CrMo4-4, 13CrMo4-5, 15CrMo3, 15CrMo5, 13CrMoV42, 15Cr3, 16MnCr5, 20MnCr5, 15CrMo5, 24CrMo5, 25CrMo4, GS-22CrMo5, GS-22CrMo54, GS 17CrMo5-5, 16CrMoV4, 42CrMo4, 42CrMo4V, 41CrMo4V
 ASTM A 182 Gr. F11 / F12; A 193 Gr. B7; A 213 Gr. T12; A 217 Gr. WC6; A 234 Gr. WP11; A335 Gr. P11, P12; A 336 Gr. F11, F12; A 426 Gr. CP12 ; A 199; A200; A 387 Gr A11 / 12

ZULASSUNGEN CE

SCHWEISSPOSITIONEN



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	Cr	Mo
	0.09	0.6	1	1.1	0.5

MECHANISCHE GÜTEWERTE	Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
					RT	-40°C	
	690°C±15°C 1h	460	560	22	80	47	HRc

RÜCKTROCKNUNG Not required

GAS ACC. EN ISO 14175 I1



CEWELD SG CrMo1 Tig

SG CRM01 TIG 1,2 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663411396

SG CRM01 TIG 1,6 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663411402

SG CRM01 TIG 2,0 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663411419

SG CRM01 TIG 2,4 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663411426

SG CRM01 TIG 3,2 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663411433