



CEWELD AA DUR 6

TYPE	Cobalt based (Stellite 6) fluxcored welding wire (FCAW) for overlay welding																			
ANWENDUNGEN	Cladding valves, Steam-valves, high temperature liquid pumps, hot cutting tools, exhaust valves, seats, cutting knives, metal to metal wear, bearing surfaces, chemical industry, hot shear blades etc.																			
EIGENSCHAFTEN	Outstanding alloy against abrasion, thermo-shock and corrosion combined with high temperatures. The weld deposit can be machined with tungsten tool tips and by grinding. The hardness of the weld deposit will decrease 16% at 300°C and about 30% at 600°C. Excellent alloy against thermal shock, abrasion, erosion, corrosion and cavitation at high temperature.																			
KLASSIFIKATION	AWS EN ISO DIN F-nr	A 5.21: ERCoCr-A 14700: T Co2 8555: MSG 20-GF-40-CTZ 71																		
GEEIGNET FÜR	ER CoCr-A Stellite 6 Celist 706																			
ZULASSUNGEN																				
SCHWEISSPOSITIONEN																				
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>Fe</th> <th>W</th> <th>Co</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>1</td> <td>0.8</td> <td>28</td> <td>2</td> <td>0.01</td> <td>3</td> <td>4.5</td> <td>Rem.</td> </tr> </tbody> </table>	C	Si	Mn	Cr	Ni	Mo	Fe	W	Co	1	1	0.8	28	2	0.01	3	4.5	Rem.	
C	Si	Mn	Cr	Ni	Mo	Fe	W	Co												
1	1	0.8	28	2	0.01	3	4.5	Rem.												
MECHANISCHE GÜTEWERTE	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>Heat Treatment</th> <th>R_{P0.2} (MPa)</th> <th>R_m (MPa)</th> <th>A5 (%)</th> <th>Hardness</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td></td> <td></td> <td></td> <td>43 HRc</td> </tr> </tbody> </table>	Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A5 (%)	Hardness	As Welded				43 HRc									
Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A5 (%)	Hardness																
As Welded				43 HRc																
RÜCKTROCKNUNG	140°C / 24 hr																			
GAS ACC. EN ISO 14175	M13																			



CEWELD AA DUR 6

AA DUR 6 0,8MM

Packaging	KG/unit	EanCode
BS-300	15	8720663402011

AA DUR 6 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663402028

AA DUR 6 1,6MM

Packaging	KG/unit	EanCode
BS-300	15	8720663402042