



CEWELD AA M410 NiMo

TYPE	Metal cored CrNiMo alloyed welding wire for rebuilding and cladding							
ANWENDUNGEN	AA M410NiMo is a Cr-Ni-Mo- alloyed, gas-shielded metal-cored wire electrode for cladding. The corrosion resistant deposit offers a medium hardness and is resistant against metal-metal wear and high surface pressure. He is used in steel mill rollers, thermoshock resistant and suitable for Francis and Pelton turbines. Used in steam power plants for its excelent resistance to cavitation and stress corrosion cracking.							
EIGENSCHAFTEN	Good corrosion and abrasion resistance as required by water turbines in hydropower plants.							
KLASSIFIKATION	AWS	A 5.22: E410NiMoT0-4						
	EN ISO	17633-A: T 13 4 M M21 2 / T 410NiMo						
	W.Nr.	1.4313						
	F-nr	6						
	FM	5						
GEEIGNET FÜR	13%Cr - 4%Ni - 0,5%Mo Steel 1.4000, 1.4001, 1.4002, 1.4313, 1.4317, 1.4407, 1.4413, 1.4414, GX4CrNi13-4, X3CrNiMo13-4, GX5CrNiMo13-4, GX4CrNiMo13-4, X 6 Cr 13, X 7 Cr 14, X 6 CrAl 13 ACI Gr. CA 6 NM							
ZULASSUNGEN								
SCHWEISSPOSITIONEN								
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	P	S	Cr	Ni	Mo
	0.06	0.8	1	0.015	0.015	12.5	4.5	0.5
MECHANISCHE GÜTEWERTE	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness	
	As Welded	800	890	19	0°C		40 HRc	
RÜCKTROCKNUNG	140°C / 24 hr							
GAS ACC. EN ISO 14175	M21							



CEWELD AA M410 NiMo

AA M410 NIMO 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663411785