

CEWELD L-Ag5P

TYPE	Copper Phosphorus Silver Brazing Alloy.	
ANWENDUNGEN	Particularly recommended for sanitary and refrigerating equipment. Suitable for working temperatures up to 200 °C	
EIGENSCHAFTEN	Excellent flowing alloy with high purity offering strong brazing joints. Do not use in a sulphurous environment. Flux/Paste: CEWELD Super-Flux	
KLASSIFIKATION	AWS	A 5.8: BCuP-3
	EN ISO	17672: CuP 281
	F-nr	103

GEEIGNET FÜR Copper to Copper (without flux). Brass, Copper and Copper-Tin Alloys (with flux).

ZULASSUNGEN

SCHWEISSPOSITIONEN



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

Cu	Ag	P
Rem.	5	6


MECHANISCHE GÜTEWERTE

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded		250		HRc

RÜCKTROCKNUNG Not required

MELTING RANGE 645 - 815°C

GAS ACC. EN ISO 14175



CEWELD L-Ag5P

L-AG5P 1,5MM

Packaging	KG/unit	EanCode
D-300	10,11	8720663421487