



# CEWELD SACW Mo

|                       |   |     |                   |        |                    |      |   |    |   |
|-----------------------|---|-----|-------------------|--------|--------------------|------|---|----|---|
| <b>TYPE</b>           | Seamless copper coated wire Type P1   |     |                   |        |                    |      |   |    |   |
| <b>ANWENDUNGEN</b>    | SA CW Mo is a cored wire for 0.5%Mo steels, i.e. P1. These steels are commonly used at service temperatures up to 500 °C and for some sub-zero structural applications.                                     |     |                   |        |                    |      |   |    |   |
| <b>EIGENSCHAFTEN</b>  | The 0.5% alloying improves creep performance compared to CMn steels and sees the alloy being used for boiler, pressure vessel and piping construction. Typical with FL 155 Flux or FL 160                   |     |                   |        |                    |      |   |    |   |
| <b>KLASSIFIKATION</b> | <table border="0"> <tr> <td>AWS</td> <td>A 5.23: F8A4-ECA1</td> </tr> <tr> <td>EN ISO</td> <td>24598-A: S T Mo FB</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>4</td> </tr> </table> | AWS | A 5.23: F8A4-ECA1 | EN ISO | 24598-A: S T Mo FB | F-nr | 6 | FM | 4 |
| AWS                   | A 5.23: F8A4-ECA1   |     |                   |        |                    |      |   |    |   |
| EN ISO                | 24598-A: S T Mo FB  |     |                   |        |                    |      |   |    |   |
| F-nr                  | 6   |     |                   |        |                    |      |   |    |   |
| FM                    | 4   |     |                   |        |                    |      |   |    |   |
| <b>GEEIGNET FÜR</b>   | S355J0, E335, P285NH, P310GH, S355J0Cu, 16Mo3, P315N - S420N, P315NH - P420NH fine grain structural steels up to S460N/P460N, large-diameter pipes up to L485MB   |     |                   |        |                    |      |   |    |   |

**ZULASSUNGEN**

**SCHWEISSPOSITIONEN**



**TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)**

| C   | Si  | Mn   | P    | S    | Mo  |
|-----|-----|------|------|------|-----|
| 0.1 | 0.2 | 0.09 | 0.02 | 0.02 | 0.5 |

**MECHANISCHE GÜTEWERTE**

| Heat Treatment  | R <sub>P0,2</sub> (MPa) | R <sub>m</sub> (MPa) | A <sub>5</sub> (%) | Impact Energy (J) ISO-V |       | Hardness |
|-----------------|-------------------------|----------------------|--------------------|-------------------------|-------|----------|
|                 |                         |                      |                    | -20°C                   | -40°C |          |
| 675°C- 705°C 1h | 490                     | 570                  | 24                 | 120                     | 80    | HRc      |

**RÜCKTROCKNUNG** Not required

**GAS ACC. EN ISO 14175**