



CEWELD S3 NiMoCr

TYPE Submerged arc welding wire for high strength fine grain steels with >690 MPa yield strength.

ANWENDUNGEN Applications will be found in the offshore industry, shipbuilding, pressure vessels, earthmoving equipment, cranes and general structural fabrication.

EIGENSCHAFTEN Welding procedure (including preheat temperature, interpass temperature and PWHT) will be dependent on the base material being welded, including its thickness, and any applicable design codes. Remarkable crack resistant weld metal in combination with very low hydrogen content. Therefore, suitable for the economic processing of high-strength and low temperature fine grained structural steels. Excellent welding properties in combination with FL 155 high basic flux even in narrow gaps. To obtain optimum mechanical properties the heat input should be kept below 15 kJ/cm and interpass temperature between 100 and 150°C.

KLASSIFIKATION

AWS	A 5.23: EM4~
EN ISO	26304-A: S3Ni2,5CrMo
F-nr	6
FM	2

GEEIGNET FÜR S690, X80, X90, X100, S690QL1, Weldom 700, Dilimax, Naxtra 70, 10CrMo9-10, 16NiCrMo12-6, high strength steels with yield >690N/mm², S500Q-S690Q, S500QL-S690QL, P500Q-P690Q, P500QL1-ASTM: A514, A517. HY80, HY100, Q1(N), Oceanfit 100, Oceanfit 690

ZULASSUNGEN CE, Lloyds

SCHWEISSPOSITIONEN



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

C	Si	Mn	P	S	Cr	Ni	Mo
0.09	0.2	1.6	0.01	0.01	0.3	2.1	0.6

MECHANISCHE GÜTEWERTE

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
				-40°C	-60°C	
As Welded	710	780	17	80	75	HRc

RÜCKTROCKNUNG Not required

GAS ACC. EN ISO 14175



CEWELD S3 NiMoCr

S3 NIMOCR 2,0MM

Packaging	KG/unit	EanCode
Drum	300	8720663404589
K-415	27	8720663404572

S3 NIMOCR 4,0MM

Packaging	KG/unit	EanCode
K-415	25	8720663404596