



CEWELD CuSn6

TYPE	Tin bronze alloy of minimally 6% tin for virtually all welding procedures.																
ANWENDUNGEN	Boilers and tubes out of copper or copper alloys, oven soldering etc.																
EIGENSCHAFTEN	Very good deoxidization. Surfacing and joining of Copper and CuSn-Alloys. Widely used in oven soldering. High quality alloyed copper wire. Sound, pore free deposits and good electrical conductivity. Excellent corrosion resistance																
KLASSIFIKATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.7: ERCuSn-A</td> </tr> <tr> <td>EN ISO</td> <td>24373: Cu 5180A / CuSn6P</td> </tr> <tr> <td>W.Nr.</td> <td>2.1022</td> </tr> <tr> <td>F-nr</td> <td>33</td> </tr> </table>	AWS	A 5.7: ERCuSn-A	EN ISO	24373: Cu 5180A / CuSn6P	W.Nr.	2.1022	F-nr	33								
AWS	A 5.7: ERCuSn-A																
EN ISO	24373: Cu 5180A / CuSn6P																
W.Nr.	2.1022																
F-nr	33																
GEEIGNET FÜR	<p>Tin bronze alloy of minimally 6% tin for virtually all welding procedures. Very good deoxidisation. Surfacing and joining of Copper and CuSn-alloys. Widely used in oven soldering.</p> <p>Mat.n: 2.1010, 2.1016, 2.1020, 2.1030, 2.1050, 2.1052, 2.1056, 2.1080, 2.1086, 2.1090, 2.1096 CuSn8, CuSn7, CuSn6, CuSn4, G-CuSn7ZnPb, G-CuSn10</p>																
ZULASSUNGEN																	
SCHWEISSPOSITIONEN																	
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1"> <thead> <tr> <th>P</th> <th>Fe</th> <th>Cu</th> <th>Zn</th> <th>Pb</th> <th>Sn</th> </tr> </thead> <tbody> <tr> <td>0.25</td> <td>0.05</td> <td>Rem.</td> <td>0.05</td> <td>0.01</td> <td>5.5</td> </tr> </tbody> </table>	P	Fe	Cu	Zn	Pb	Sn	0.25	0.05	Rem.	0.05	0.01	5.5				
P	Fe	Cu	Zn	Pb	Sn												
0.25	0.05	Rem.	0.05	0.01	5.5												
MECHANISCHE GÜTEWERTE	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{p0,2} (MPa)</th> <th rowspan="2">R_m (MPa)</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th colspan="2">RT</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td></td> <td>260</td> <td>20</td> <td colspan="2">32</td> <td>80 HB</td> </tr> </tbody> </table>	Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness	RT		As Welded		260	20	32		80 HB
Heat Treatment	R _{p0,2} (MPa)					R _m (MPa)	A ₅ (%)		Impact Energy (J) ISO-V		Hardness						
		RT															
As Welded		260	20	32		80 HB											
RÜCKTROCKNUNG	Not required																
GAS ACC. EN ISO 14175	I1, I3																



CEWELD CuSn6

CUSN6 0,8MM

Packaging	KG/unit	EanCode
D-200	5	8720663408495
D-300	15	8720663408501

CUSN6 1,0MM

Packaging	KG/unit	EanCode
D-200	5	8720663408518
D-300	15	8720663408525
Drum	250	8720663408532

CUSN6 1,2MM

Packaging	KG/unit	EanCode
D-300	15	8720663408556
D-300	15	8720663408549

CUSN6 1,6MM

Packaging	KG/unit	EanCode
BS-300	15	8720663408563
BS-300	15	8720663408570
Drum	250	8720663408587