

CEWELD Powder 8812-Ni

TYPE	Carbide powder, agglomerated and sintered	
ANWENDUNGEN	carbide powder for wear resistant coatings produced by flame-, plasma or high velocity- flame-spraying (HVOF). Tungsten-Carbide-Nickel-coatings are resistant to abrasion and oxidation. In comparison with WC-Co layers they show an improved corrosion resistance in aqueous solutions. Plasma sprayed coatings can achieve a hardness of up to 1000 HV0.1 and tensile strength acc. to DIN 50160 of 60 N/mm ² . The maximum operating temperature is 750°C.	
EIGENSCHAFTEN	Crystal size of WC Apparent Density (ISO 3923-2) Particle Size Range in µm Particle Shape 2.5 µm FSSS4.3 – 5.4 g/cm ² 2/5 – 38/15 – 53/22 Preponderant spherical	
KLASSIFIKATION	EN ISO	14232-1 WC-Ni 88/12
GEEIGNET FÜR	Augers, impellers, shafts, hydraulics, pulling equipment, fan blades etc.	
ZULASSUNGEN		
SCHWEISSPOSITIONEN		
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	Ni	WC
	12	88
MECHANISCHE GÜTEWERTE		
RÜCKTROCKNUNG	Not required	
GAS ACC. EN ISO 14175	None	