



# CEWELD SACW CrMo1V

**TYPE** High- basicity flux-cored wire for submerged-arc welding. (Typ CrMo1V, 1.7745)

**ANWENDUNGEN** CEWELD® SACW CrMo1V is a basic cored wire with Excellent weld puddle manipulation. Low spatter loss, easy slag removal. Extremely crack resistant. Suitable for economic welding of CrMoV-steels up to 550 °C. With Flux CEWELD FL155

**EIGENSCHAFTEN** Foundries, production welding

**KLASSIFIKATION**

AWS	A 5.23: G (~EB2V)
EN ISO	24598-A: ST G (~CrMo1V)
W.Nr.	~1.7745
F-nr	6
FM	4

**GEEIGNET FÜR** **Typ 1Cr0,5Mo,V ISO 15608: ~5,1**  
 1.7335, 1.7262, 1.7728, 1.7218, 1.7225, 1.7258, 1.7354, 1.7357, 1.7745, 1.7706, 1.7733  
 13CrMo4-5, 15CrMo5, 15 CrMoV 5 10, 16CrMoV4, 25CrMo4, 42CrMo4, 24CrMo5, G22CrMo5-4,  
 G17CrMo5-5, 24CrMoV5-5, G17CrMoV5-10  
 ASTM A 182 Gr. F12; A 193 Gr. B7; A 213 Gr. T12; A 217 Gr. WC6; A 234 Gr. WP11; A335 Gr. P11,  
 P12; A 336 Gr. F11, F12; A 426 Gr. CP12

**ZULASSUNGEN**

**SCHWEISSPOSITIONEN**



**TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)**

C	Si	Mn	P	S	Cr	Ni	Mo	V
0.12	0.25	0.85	0.02	0.02	1.25	0.3	1.1	0.25

**MECHANISCHE GÜTEWERTE**

Heat Treatment	R <sub>PO,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Impact Energy (J) ISO-V		Hardness
				RT		
690°C±15°C 6h	550	700	20	70		HRc

**RÜCKTROCKNUNG** Not required

**GAS ACC. EN ISO 14175**