



CEWELD SG 1 Tig

TYPE Copper coated welding wire developed for Tig welding of un and -low alloyed steels with low silicon and manganese content.

APPLICATIONS CEWELD® SG 1 Tig is a Tig Rod for joining and surfacing unalloyed and low-alloy structural steels. Typical areas of application are shipbuilding, tank and plant construction

PROPERTIES CEWELD® SG 1 Tig is extremely easy to weld with excellent welding properties. Due to its low silicon content, it is suitable for welding galvanized sheet metal or weld seams that subsequently have to be galvanized.

CLASSIFICATION

AWS	A 5.18: ER 70S-3
EN ISO	636-A: W 42 4 2Si
F-nr	6
FM	1

SUITABLE FOR **Rp< 420 MPa (60ksi) ISO 15608: 1.1(ReH < 275 MPa), 1.2 (275 < ReH < 360 MPa), 1.3 (ReH > 360 MPa < 420 MPa)**
 1.0035, 1.0038, 1.0039, 1.0044, 1.0112, 1.0116, 1.0130, 1.0145, 1.0253, 1.0254, 1.0255, 1.0258, 1.0259, 1.0319, 1.0345, 1.0345, 1.0345, 1.0348, 1.0352, 1.0418, 1.0420, 1.0425, 1.0425, 1.0425, 1.0451, 1.0452, 1.0453, 1.0457, 1.0459, 1.0460, 1.0461, 1.0486, 1.0490, 1.0491, 1.0619, 1.1100, 1.0409, 1.0421, 1.0426, 1.0429, 1.0430, 1.0436, 1.0473, 1.0481, 1.0482, 1.0484, 1.0505, 1.0545, 1.0546, 1.0562, 1.0566, 1.0570, 1.0578, 1.0581, 1.0582, 1.8902, 1.8912, 1.8932
 10Ni14, 12Ni14, 13MnNi6-3, 15NiMn6,
 S235JR-S355JR, S235JO-S355JO, P195TR1-P265TR1, P195GH-P265GH, L245NB-L360NB, L245MB-L360MB, L415NB, L415MB, WStE 380, WStE 420, S420NL
 A, B, D, E, A 32-E 36
ASTM A 105, A 106, Gr. A, B; A 283 Gr. A, C; A 285 Gr. A, B, C; A 501, Gr. B; A 573, Gr. 58, 65, 70; A 633, Gr. A, C; A 711 Gr. 1013;
API 5 L Gr. B, X42, X52, X60
 Domex 315-420MC, MC Plus, ML

APPROVALS CE

WELDING POSITIONS

TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	P	S	Cr	Ni	Mo	V	Cu	Al	Ti+Zr
	0.08	0.6	1.1	0.009	0.014	0.06	0.03	0.01	0.003	0.03	0.003	0.012

MECHANICAL PROPERTIES	Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
					-20°C	-46°C	
	As Welded	470	560	30	245	100	HRC

REDRYING Not required

GAS ACC. EN ISO 14175 I1



CEWELD SG 1 Tig

SG 1 TIG 1,6 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663411198

SG 1 TIG 2,0 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663411204

SG 1 TIG 2,4 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663411211

SG 1 TIG 3,0 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663411273

SG 1 TIG 3,2 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663411228