



CEWELD AA M410 NiMo

TYPE	Metal cored CrNiMo alloyed welding wire for rebuilding and cladding																
APPLICATIONS	AA M410NiMo is a Cr-Ni-Mo- alloyed, gas-shielded metal-cored wire electrode for cladding. The corrosion resistant deposit offers a medium hardness and is resistant against metal-metal wear and high surface pressure. He is used in steel mill rollers, thermoshock resistant and suitable for Francis and Pelton turbines. Used in steam power plants for its excelent resistance to cavitation and stress corrosion cracking.																
PROPERTIES	Good corrosion and abrasion resistance as required by water turbines in hydropower plants.																
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.22: E410NiMoT0-4</td> </tr> <tr> <td>EN ISO</td> <td>17633-A: T 13 4 M M21 2 / T 410NiMo</td> </tr> <tr> <td>W.Nr.</td> <td>1.4313</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>5</td> </tr> </table>	AWS	A 5.22: E410NiMoT0-4	EN ISO	17633-A: T 13 4 M M21 2 / T 410NiMo	W.Nr.	1.4313	F-nr	6	FM	5						
AWS	A 5.22: E410NiMoT0-4																
EN ISO	17633-A: T 13 4 M M21 2 / T 410NiMo																
W.Nr.	1.4313																
F-nr	6																
FM	5																
SUITABLE FOR	13%Cr - 4%Ni - 0,5%Mo Steel 1.4000, 1.4001, 1.4002, 1.4313, 1.4317, 1.4407, 1.4413, 1.4414, GX4CrNi13-4, X3CrNiMo13-4, GX5CrNiMo13-4, GX4CrNiMo13-4, X 6 Cr 13, X 7 Cr 14, X 6 CrAl 13 ACI Gr. CA 6 NM																
APPROVALS																	
WELDING POSITIONS																	
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> </tr> </thead> <tbody> <tr> <td>0.06</td> <td>0.8</td> <td>1</td> <td>0.015</td> <td>0.015</td> <td>12.5</td> <td>4.5</td> <td>0.5</td> </tr> </tbody> </table>	C	Si	Mn	P	S	Cr	Ni	Mo	0.06	0.8	1	0.015	0.015	12.5	4.5	0.5
C	Si	Mn	P	S	Cr	Ni	Mo										
0.06	0.8	1	0.015	0.015	12.5	4.5	0.5										
MECHANICAL PROPERTIES	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{P0,2} (MPa)</th> <th rowspan="2">R_m (MPa)</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th colspan="2">0°C</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>800</td> <td>890</td> <td>19</td> <td colspan="2">67</td> <td>40 HRc</td> </tr> </tbody> </table>	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness	0°C		As Welded	800	890	19	67		40 HRc
Heat Treatment	R _{P0,2} (MPa)					R _m (MPa)	A ₅ (%)		Impact Energy (J) ISO-V		Hardness						
		0°C															
As Welded	800	890	19	67		40 HRc											
REDRYING	140°C / 24 hr																
GAS ACC. EN ISO 14175	M21																



CEWELD AA M410 NiMo

AA M410 NIMO 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663411785