



CEWELD AA CrCoMo 46

TYPE High-alloyed tubular wire on a Cr-Co-Mo basis for high temperature applications.

APPLICATIONS The characteristics of the deposit are comparable with cobalt-base alloys in terms of thermal shock and corrosion resistance that makes this alloy applicable for overlaying parts that are subject to high temperatures combined with corrosion attack, wear and thermal shock combinations. AA CrCoMo 46 can be used as intermediate layer against metal to metal wear at high pressure loads.

PROPERTIES Very good corrosion resistance combined with excellent hardness properties at temperatures up to 650°C. Scale resistant till 900°C and excellent strength at high working temperatures. Excellent weldability and often used as economical alternative for „stellite“

CLASSIFICATION EN ISO 14700: T Fe3

SUITABLE FOR Hot rolling parts for continuous casting, hotpress tools, pump parts, sleeves, mandrels, forging hammers, chemical and glass industry.

APPROVALS

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

MECHANICAL PROPERTIES

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness
As Welded				47 HRc

REDRYING 140°C / 24 hr

GAS ACC. EN ISO 14175 M21