

# CEWELD Universal-Flux

TYPE	Universal flux for brazing with brass and new Silver alloy
APPLICATIONS	Copper, Copper Alloys, Brass, Steel, Galvanized steel
PROPERTIES	Working temperature from 550-800 °C
CLASSIFICATION	AWS A 5.31: FB3-F EN ISO 18496: FH10
SUITABLE FOR	Universal flux for brazing with brass and new silver alloy on copper, copper alloys, brass, steel, galvanized steel, working temperature from 550-800 °C.
APPROVALS	
WELDING POSITIONS	
(%)	
MECHANICAL PROPERTIES	
REDRYING	Not required
GAS ACC. EN ISO 14175	