

ТҮРЕ	CuZnNi high strength flux coated brazing alloy.					
APPLICATIONS	Joining: Steels, Galvanized steel, Tempered Cast Iron, Cast iron, Nickel alloys etc. This alloy is mainly used in the furniture and the bicycle industry for high strength joining of steels, also is this alloy recommended for rebuilding cock wheels due to the good sliding properties.					
PROPERTIES	High strength brass alloy containing Nickel for more strength and bridging capability during brazing. Due to the special flux coating this type is mostly used in maintenance and repair, the flux coated rod can be bended very well without loosing flux.					
CLASSIFICATION	EN ISO W.Nr.	A 5.8: RBCuZn-D 17672: Cu 773 2.0711 106				
SUITABLE FOR	Steels, Galvanized steel, Tempered Cast Iron, Cast iron, Nickel alloys					
APPROVALS						
WELDING POSITIONS	PA PB PC PD PE PE PG					
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	Si		Ni		Cu	
	0.1		10		48	
MECHANICAL PROPERTIES	Heat Treatment	R <sub>P0,2</sub> (MPa)	Rm (MPa)	A5 (%)	Hardness	
	As Welded		800		180 HB	
REDRYING	Not required					
MELTING RANGE	890 - 920°C					
GAS ACC. EN ISO 14175	11					

Certilas THE FILLER METAL SPECIALIST