



CEWELD E CuNi30Mn

TYPE	Copper-Nickel based stick electrode (SMAW)								
APPLICATIONS	Wrought or cast copper nickel alloys, marine applications, desalination equipment.								
PROPERTIES	Excellent corrosion resistance in seawater and against fouling. Suitable for dissimilar welding of Monel Alloy 450 to Nickel 200 and or other Copper -Nickel alloys. Small diameters can be used in all positions.								
CLASSIFICATION	<table border="0" style="width: 100%;"> <tr> <td style="width: 33%;">AWS</td> <td>A 5.6: E CuNi</td> </tr> <tr> <td>EN ISO</td> <td>17777: E Cu 7158</td> </tr> <tr> <td>W.Nr.</td> <td>2.0838</td> </tr> <tr> <td>F-nr</td> <td>34</td> </tr> </table>	AWS	A 5.6: E CuNi	EN ISO	17777: E Cu 7158	W.Nr.	2.0838	F-nr	34
AWS	A 5.6: E CuNi								
EN ISO	17777: E Cu 7158								
W.Nr.	2.0838								
F-nr	34								

SUITABLE FOR **Cu7158 (CuNi30Mn2FeTi), 2.0838**
Mat.n: 2.0878, 2.0882,
(Monel 67): Wrought and Cast Alloys of 70-30, 80-20 and 90-10 Copper Nickel Alloys, Monel Alloy 450, Nickel 200, CuNi10Fe, CuNi20Fe (2.0878), CuNi30Fe (2.0882).

APPROVALS

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

Si	Mn	Ti	Fe	Ni+Co	Cu
0.25	1	0.25	0.55	30	Rem.

MECHANICAL PROPERTIES

Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded		360	30	HRc

REDRYING Not required

GAS ACC. EN ISO 14175



CEWELD E CuNi30Mn

E CUNI30MN 2,4 X 305MM

Packaging	KG/unit	EanCode
Can	4,54	8720663419170

E CUNI30MN 3,2 X 356MM

Packaging	KG/unit	EanCode
Can	4,54	8720663419187