



# CEWELD FL 160

**TYPE** High basic SAW flux with low hydrogen content.

**APPLICATIONS** Boiler works, vessel and structural steel works, tanks and pressure vessels, offshore lifting applications, platforms etc..

**PROPERTIES** FL 160 is a highly basic SAW flux with low hydrogen content. Basicity: about 3 (according to Boniszewski) Current: DC or AC, in single or multi-wires Grain size: 2-20

**CLASSIFICATION** EN ISO 14174: SA FB 1 55 AC H5

**SUITABLE FOR** S355, S420, S460, X65, X70, X80

**APPROVALS**

**WELDING POSITIONS**



**TYPICAL CHEMICAL COMPOSITION IN WEIGHT (%)**

Al2O3	CaF2	SiO2	CaO+MgO
20	20	15	40

**MECHANICAL PROPERTIES**

**REDRYING** Not required

**GAS ACC.** EN ISO 14175



# CEWELD FL 160

FL 160 0,2 - 2,0MM

Packaging	KG/unit	EanCode
Bag	25	8720663404008
Bag	25	8720663404015