



| TYPE  | Welding wire for rebuilding parts and for buffer layers before hardfacing.  |     |                            |             |           |     |          |  |
|---|---|-----|----------------------------|-------------|-----------|-----|----------|--|
| APPLICATIONS  | Rebuilding machine parts before Hardfacing and cladding crane and or train wheels to achieve a wear resistant layer against high pressure caused by metal to metal friction.  |     |                            |             |           |     |          |  |
| PROPERTIES  | CEWELD MA 350 offers almost full hardness in the first layer and can be applied without any risk of cracking. Multiple layers or sandwich layers are possible before Hardfacing and will help to increase the hardness (wear resistance) from the hardface layer. |     |                            |             |           |     |          |  |
| CLASSIFICATION  | AWSA 5.21: ERFe-1EN ISO14700: S Fe2DIN8555: MSG-5-GZ-350W.Nr.~1.7363F-nr71  |     |                            |             |           |     |          |  |
| SUITABLE FOR  | 350 HB hardfaing alloy, sprocket wheels, rebuilding, crushing hammers, Rebuilding machine parts<br>before hardfacing and cladding crane and or train wheels to achieve a wear resistant layer against<br>high pressure caused by metal to metal friction.         |     |                            |             |           |     |          |  |
| APPROVALS   |   |     |                            |             |           |     |          |  |
| WELDING POSITIONS                                       |   |     |                            |             |           |     |          |  |
| TYPICAL CHEMICAL<br>ANALYSIS OF THE FILLER<br>METAL (%) | С   | Mn  | Cr                         | Ni          |           | Мо  | Fe       |  |
|   | 0.08  | 0.5 | 6                          | 0.1         |           | 0.5 | Rem.     |  |
| MECHANICAL PROPERTIES                                   | Heat<br>Treatment   |     | R <sub>P0,2</sub><br>(MPa) | Rm<br>(MPa) | A5<br>(%) | H F | lardness |  |
|   | As Welded   |     |                            |             |           |     | 360 HB   |  |
| REDRYING  | Not required  |     |                            |             |           |     |          |  |
| GAS ACC. EN ISO 14175                                   | M21   |     |                            |             |           |     |          |  |





## CEWELD MA 350

| MA 350 0,8MM | Packaging | KG/unit | EanCode       |
|--------------|-----------|---------|---------------|
|              | BS-300    | 15      | 8720663403056 |
|              |           |         |               |
| MA 350 1,0MM | Packaging | KG/unit | EanCode       |
|              | BS-300    | 15      | 8720663403063 |
|              |           |         |               |
| MA 350 1,2MM | Packaging | KG/unit | EanCode       |
|              | BS-300    | 15      | 8720663403070 |
|              |           |         |               |
| MA 350 1,6MM | Packaging | KG/unit | EanCode       |
|              | BS-300    | 15      | 8720663403094 |