



# CEWELD AA M500

TYPE	Seamless metal cored wire for welding S460 - X70 type steels																
APPLICATIONS	Crane, steel, vessel and apparatus construction, offshore, lifting, drilling platforms etc.																
PROPERTIES	CEWELD® AA M500 is a seamless metal cored wire with remarkable stable arc and no spatters. Excellent for use in automated welding applications such as orbital Mag or robotic welding. This wire offers a unique welding deposit with less than 1% nickel to full fill NACE requirements and cover more procedures up to 500 MPa yield strength steels. CEWELD® AA M500 can also be used for constructions that needs post weld heat treatment after welding and still offers mechanical properties confirming 5Y46 class. Due to the seamless production process the hydrogen content is below 3ml/100gr weld metal even after long storage in unconditioned condition.																
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.28: E80C-Ni1 H4</td> </tr> <tr> <td>EN ISO</td> <td>17632-A: T 50 6 1Ni M M21 1 H5</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>1</td> </tr> </table>	AWS	A 5.28: E80C-Ni1 H4	EN ISO	17632-A: T 50 6 1Ni M M21 1 H5	F-nr	6	FM	1								
AWS	A 5.28: E80C-Ni1 H4																
EN ISO	17632-A: T 50 6 1Ni M M21 1 H5																
F-nr	6																
FM	1																
SUITABLE FOR	<p><b>Reh ≤ 500 MPa ISO 15608: 1.3, ~3.1, ~2.2, 2.1,</b>            1.0580 to 1.0070, 1.8900 to 1.8905, 1.8930 to 1.8935, 1.8910 to 1.8915, 1.6217, 1.6210, 1.0481, 1.0482, 1.0551, 1.0553.</p> <p>S275N-S460N, S275NL-S460NL, S275M-S460M, S275ML-S460ML, P355N, P355NH, P460N, P460NH, P275NL1-P460NL1, P275NL2- P460NL2, L360NB, L415NB, L360MB-L450MB, L360QB-L450QB</p> <p>ASTM A 203 Gr. D, E; A 350 Gr. LF1, LF2, LF3; A 420 Gr. WPL3, WPL6; A 516 Gr. 60, 65, 70; A 572 Gr. 42, 50, 55, 60, 65; A 633 Gr. A, D, E; A 662 Gr. A, B, C; A 707 Gr. L1, L2, L3; A 738 Gr. A; A 841 A, B, C; API 5 L X52, X60, X65, X52Q, X60Q, X65Q</p> <p>Oceanfit 52, Oceanfit 60, Oceanfit 65, Oceanfit 355, Oceanfit 420, Oceanfit 460, alform plate 460M; durostat 400, 450, 500, durostat B2</p>																
APPROVALS	CE																
WELDING POSITIONS																	
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Ni</th> </tr> </thead> <tbody> <tr> <td>0.05</td> <td>0.7</td> <td>1.5</td> <td>0.015</td> <td>0.015</td> <td>0.9</td> </tr> </tbody> </table>	C	Si	Mn	P	S	Ni	0.05	0.7	1.5	0.015	0.015	0.9				
C	Si	Mn	P	S	Ni												
0.05	0.7	1.5	0.015	0.015	0.9												
MECHANICAL PROPERTIES	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R<sub>P0.2</sub> (MPa)</th> <th rowspan="2">R<sub>m</sub> (MPa)</th> <th rowspan="2">A<sub>5</sub> (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th>-40°C</th> <th>-60°C</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>550</td> <td>690</td> <td>26</td> <td>80</td> <td>60</td> <td>HRc</td> </tr> </tbody> </table>	Heat Treatment	R <sub>P0.2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Impact Energy (J) ISO-V		Hardness	-40°C	-60°C	As Welded	550	690	26	80	60	HRc
Heat Treatment	R <sub>P0.2</sub> (MPa)					R <sub>m</sub> (MPa)	A <sub>5</sub> (%)		Impact Energy (J) ISO-V		Hardness						
		-40°C	-60°C														
As Welded	550	690	26	80	60	HRc											
REDRYING	Not required																
GAS ACC. EN ISO 14175	M21																



# CEWELD AA M500

AA M500 1,2MM

Packaging	KG/unit	EanCode
BS-300	16	8720663423405