





TYPE CEWELD® AA 410 is a stainless flux cored wire for Hardfacing.(13% Cr Steel)

APPLICATIONS Overlay of carbon and low-alloy steels for resistance to corrosion, erosion, or abrasion.

PROPERTIES CEWELD® AA 410 has higher hardness and is used in valve seats to obtain better galling resistance.

Normally to obtain adequate ductility, preheat and post-weld heat-treatment are required .

CEWELD® AA 410 is a martensitic stainless steel that is heat-treatable. It has a nominal weld metal composition of 12% Chromium. These weld deposits are air hardenable that can normally be heat-

treated after welding

CLASSIFICATION **AWS** A 5.22: E410T0-4

> EN ISO 14700: T Fe7

W.Nr. 1.4009

SUITABLE FOR Ferritic 13 % Chrome steel,

> 1.4000, 1.4001, 1.4002, 1.4003, 1.4006, 1.4008, 1.4021, 1.4024, X6Cr13, X6CrAl13, X10Cr13, X15Cr13, X20Cr13, G-X10Cr13

AISI 410, 420

APPROVALS

WELDING POSITIONS



TYPICAL CHEMICAL

ANALYSIS OF WELD METAL

(%)

| С | Si | Mn | Р | Cr | Мо |
|------|-----|-----|-------|------|-----|
| 0.12 | 0.8 | 1.2 | 0.015 | 13.5 | 0.5 |

MECHANICAL PROPERTIES

| Heat | R _{P0,2} | Rm | A5 | Hardness |
|-----------|-------------------|-------|-----|----------|
| Treatment | (MPa) | (MPa) | (%) | |
| As Welded | | | | 330 HB |

REDRYING Not required

GAS ACC. EN ISO 14175 M21





CEWELD AA 410

AA 410 1,2MM

| Packaging | KG/unit | EanCode | | |
|-----------|---------|---------------|--|--|
| BS-300 15 | | 8720663413826 | | |