



CEWELD E 9015-B9

TYPE Basic, Cr and Mo-alloyed electrode for heat resistant steels T/P91

APPLICATIONS CEWELD® E 9015-B9 is a basic stick electrode for modified 9Cr1Mo steels. The weld metal of type 9Cr-1Mo-VNb is characterized by a martensitic microstructure and is suitable for applications in the tempered condition. The range of applications includes joint welding of similar heat-resistant steels and cast steel in turbine and power plant construction as well as in the chemical industry.

PROPERTIES The weld metal of CEWELD® E 9015-B9 has a very low hydrogen content and is suitable for application temperatures up to max. 650° C in the long-term range. Preheating and interpass temperature 250 - 350° C, then tempering 750° C / >2h. It can be welded in a short arc in all positions, vertical down.

CLASSIFICATION

AWS	A 5.5: E9015-B91
EN ISO	3580-A: E CrMo91 B42 H5
F-nr	4
FM	4

SUITABLE FOR **9%Cr, 1%Mo, VNb**
 1.7389, 1.7386, 1.4922, 1.4935, 1.4904, 1.4903, 1.4955,
 X11CrMo9-1, X12CrMo9.1, X20CrMoV10-1, X10CrMoVNb9-1, GX12CrMoVNbN9-1
 ASTM Grade 91, T91, P91, F91, FP91, WP91, C12A
 STPA28, STBA28

APPROVALS CE

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

C	Si	Mn	P	S	Cr	Ni	Mo	V	Nb	N
0.1	0.3	0.8	0.008	0.008	9	0.65	0.99	0.2	0.05	0.05

MECHANICAL PROPERTIES

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
				RT		
760°C±15°C 2h	560	750	18	60		HRc

REDRYING 300°C / 2 hr

GAS ACC. EN ISO 14175