



CEWELD E 7028

TYPE	High recovery (180%) basic electrode																
APPLICATIONS	High efficiency heavy coated basic type electrode Suitable for medium section steel fabrication, tanks building, shipyards and in general where a high speed welding is required.																
PROPERTIES	Suitable for downhand butt- and fillet weld, smooth welding pool without spatter loss, easy slag release, very nice bead surface																
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.1: E 7028</td> </tr> <tr> <td>EN ISO</td> <td>2560-A: E 42 2 B 83</td> </tr> <tr> <td>F-nr</td> <td>1</td> </tr> <tr> <td>FM</td> <td>1</td> </tr> </table>	AWS	A 5.1: E 7028	EN ISO	2560-A: E 42 2 B 83	F-nr	1	FM	1								
AWS	A 5.1: E 7028																
EN ISO	2560-A: E 42 2 B 83																
F-nr	1																
FM	1																
SUITABLE FOR	<p>Rp < 420 MPa (60ksi) ISO 15608: 1.1 ReH < 275 MPa, 1.2 275 < ReH < 360 MPa , (1.3 ReH > 360 MPa < 420 MPa)</p> <p>1.0345, 1.0345, 1.0348, 1.0352, 1.0418, 1.0420, 1.0425, 1.0425, 1.0425, 1.0451, 1.0452, 1.0453, 1.0457, 1.0459, 1.0460, 1.0460, 1.0461, 1.0486, 1.0490, 1.0491, 1.0619, 1.1100, 1.0409, 1.0421, 1.0426, 1.0429, 1.0430, 1.0436, 1.0473, 1.0481, 1.0482, 1.0484, 1.0505, 1.0545, 1.0546, 1.0562, 1.0566, 1.0570, 1.0578, 1.0581, 1.0582, 1.8902, 1.8912, 1.8932</p> <p>10Ni14, 12Ni14, 13MnNi6-3, 15NiMn6,</p> <p>S235JR-S355JR, S235JO-S355JO, S450JO, S235J2-S355J2, S275N-S460N, S275M-S460M, P235GH-P355GH, P275NL1-P460NL1, P215NL, P265NL, P355N, P285NH-P460NH, P195TR1-P265TR1, P195TR2-P265TR2, P195GH-P265GH, L245NB-L415NB, L450QB, L245MB-L450MB, GE200-GE240,</p> <p>A, B, D, E, A 32-E 36</p> <p>ASTM A 106 Gr. A, B, C; A 181 Gr. 60, 70; A 283 Gr. A, C; A 285 Gr. A, B, C; A 350 Gr. LF1; A 414 Gr. A, B, C, D, E, F, G; A 501 Gr. B; A 513 Gr. 1018; A 516 Gr. 55, 60, 65, 70; A 573 Gr. 58, 65, 70; A 588 Gr. A, B; A 633 Gr. C, E; A 662 Gr. B; A 711 Gr. 1013; A 841 Gr. A; API 5 L Gr. B, X42, X52, X56, X60, Domex 315-420MC, MC Plus, ML</p>																
APPROVALS	CE																
WELDING POSITIONS																	
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> </tr> </thead> <tbody> <tr> <td>0.07</td> <td>0.5</td> <td>1.2</td> </tr> </tbody> </table>	C	Si	Mn	0.07	0.5	1.2										
C	Si	Mn															
0.07	0.5	1.2															
MECHANICAL PROPERTIES	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{P0.2} (MPa)</th> <th rowspan="2">R_m (MPa)</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th colspan="2">-20°C</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>430</td> <td>530</td> <td>26</td> <td colspan="2">60</td> <td>HRc</td> </tr> </tbody> </table>	Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness	-20°C		As Welded	430	530	26	60		HRc
Heat Treatment	R _{P0.2} (MPa)					R _m (MPa)	A ₅ (%)		Impact Energy (J) ISO-V		Hardness						
		-20°C															
As Welded	430	530	26	60		HRc											
REDRYING	300°C / 2 hr																
CURRENT TYPE:	DC+																
GAS ACC. EN ISO 14175																	



CEWELD E 7028

E 7028 3,2 X 450MM

Packaging	KG/unit	EanCode
Vacuum	2,2	8720682050828

E 7028 4,0 X 450MM

Packaging	KG/unit	EanCode
Vacuum	2,0	8720682050835

E 7028 5,0 X 450MM

Packaging	KG/unit	EanCode
Vacuum	2,3	8720682050842