


CEWELD NiCro 72

TYPE	Nickel Chromium solid MIG wire									
APPLICATIONS	CEWELD® NiCro 72 filler metal is a typical alloy for cladding 671/800HT tubes. Also for overlaying of carbon steels and stainless steels to get a nickel-chromium corrosion resistance surface.									
PROPRIÉTÉS	Due to the high Chromium content it has excellent resistance to high temperature corrosion, also in fuel-ash atmospheres containing sulfur and vanadium									
CLASSIFICATION	AWS	A 5.14: ERNiCr-4								
	EN ISO	18274: S Ni 6072 (NiCr44Ti)								
	F-nr	46								
	FM	6								
CONVIENT POUR	ASTM B163, B166, B167, B168 with UNS N06690, IN657, Incoloy 671/800H									
AGRÉMENTS										
POSITIONS DE SOUDAGE	     									
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL D'APPORT (%)	C	Si	Mn	P	S	Cr	Ni	Ti	Fe	Cu
	0.05	0.1	0.1	0.008	0.008	45	55	0.6	0.2	0.2
PROPRIÉTÉS MÉCANIQUES	Heat Treatment			R _{P0,2} (MPa)		R _m (MPa)		A5 (%)	Hardness	
	As Welded					700		30	HRc	
ETUVAGE	Not required									
GAS ACC. EN ISO 14175	I1									



CEWELD NiCro 72

NICRO 72 1,0MM

Packaging	KG/unit	EanCode
BS-300	13,60	8720663419088