



CEWELD G 50

TYPE Copper coated welding wire for MAG welding of un and -low alloyed steels with high yield strength

APPLICATIONS construction, offshore, car-plate welding, shipbuilding, piping, root welding, bridges, repair, etc...

PROPRIÉTÉS Extreme easy to weld with excellent welding properties and increased yield strength. High world wide excepted quality with controlled cast and helix for semi and or semi-automatic applications. Weldable with Co2 and Mix gas.

CLASSIFICATION

AWS	A 5.18: ER 70S-6
EN ISO	14341-A: G 50 5 M 4Si1
W.Nr.	1.5130
F-nr	6
FM	1

CONVIENT POUR Re ≤460 MPa (67 ksi) ISO 15608: 1.1, 1.2, 1.3, 2.1
 S235JR-S355JR, S235JO-S355JO, S450JO, S235J2-S355J2, S275N-S460N, S275M-S460M, P235GH-P355GH, P275NL1-P460NL1, P215NL, P265NL, P355N, P285NH-P460NH, P195TR1-P265TR1, P195TR2-P265TR2, P195GH-P265GH, L245NB-L415NB, L450QB, L245MB-L450MB, GE200-GE240,
 A, B, D, E, A 32-E 36
 ASTM: A 106 Gr. A, B, C; A 181 Gr. 60, 70; A 283 Gr. A, C; A 285 Gr. A, B, C; A 350 Gr. LF1; A 414 Gr. A, B, C, D, E, F, G; A 501 Gr. B; A 513 Gr. 1018; A 516 Gr. 55, 60, 65, 70; A 573 Gr. 58, 65, 70; A 588 Gr. A, B; A 633 Gr. C, E; A 662 Gr. B; A 711 Gr. 1013; A 841 Gr. A; API 5 L Gr. B, X42, X52, X56, X60, X65

AGRÉMENTS CE

POSITIONS DE SOUDAGE



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

C	Si	Mn	P	S	Cr	Ni	Mo	Cu	V	Ti+Zr
0.08	0.9	1.67	0.01	0.01	0.04	0.02	0.005	0.11	0.001	0.013

PROPRIÉTÉS MÉCANIQUES

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
				-50°C		
As Welded	560	700	18	60		HRc

ETUVAGE Not required

GAS ACC. EN ISO 14175 M21



CEWELD G 50

G 50 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663424556
Drum	250	8720663407115