



CEWELD L-Ag40Sn

TYPE High silver containing cadmium free brazing alloy

APPLICATIONS Brazing a weight range of different metals in maintenance and repair with excellent strength, Boiler

making, tubing, cooling equipment etc. Do not use this alloy above working temperatures of 200 $^{\circ}\text{C}$.

PROPRIÉTÉS Universal silver brazing alloy without Cadmium with extreme low operating temperature and high

mechanical properties. Due to the addition of Sn. this alloy will show a bright looking joint and is

more capillary then the standard silver brazing alloys.

Flux/Paste: CEWELD Super-Flux

CLASSIFICATION AWS A 5.8: BAg-28

EN ISO 17672: Ag 140

CONVIENT POUR Brazing: Steels, Copper, Copper alloys, Stainless steel, Nickel and Nickel alloys. Also suitable for

dissimilar joints between these metals.

AGRÉMENTS

POSITIONS DE SOUDAGE



TYPICAL CHEMICAL
ANALYSIS OF THE FILLER

METAL (%)

Cu	Zn	Sn	Ag
30	28	2	40

PROPRIÉTÉS MÉCANIQUES

Heat	R _{P0,2}	Rm	A5	Hardness
Treatment	(MPa)	(MPa)	(%)	
As Welded		400		HRc

ETUVAGE Not required

MELTING RANGE 650 - 710°C

GAS ACC. EN ISO 14175