



CEWELD S2Si

TYPE Solid wire for submerged arc welding up to 420 MPa yield strength structural steels

APPLICATIONS Shipbuilding, piping, root welding, bridges, repair, construction, offshore, etc.

PROPRIÉTÉS Solid drawn and rolled SAW wire with copper coating for improved current carrying capacity. S2 wire can be used with FL 180, FL188, FL 155 and FL 851 depending on the requirements and application.

CLASSIFICATION

AWS	A 5.17: EM12K
EN ISO	14171-A: S2Si
F-nr	6
FM	1

CONVIENT POUR A, B, D, E, St 37 - St 52-3, DIN 17 100, H I, H II, 17Mn4, 16Mo5, DIN 17 155, StE 255 - StE 355, DIN 17 102, GS-38, GS-60, DIN 1681, St 35.8, St 45.8, DIN 17 175, St 37.0 - St 52.0, DIN 1626 / 1629, St 37.4 - St 52.4, DIN 1628 / 1630, StE 290.7 TM - StE 360.7 TM, DIN 17 172, X 52

AGRÉMENTS CE

POSITIONS DE SOUDAGE



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

C	Si	Mn	P	S
0.1	0.3	1.1	0.015	0.015

PROPRIÉTÉS MÉCANIQUES

Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
				0°C	-20°C	
As Welded	460	600	22	60	50	HRC

ETUVAGE Not required

GAS ACC. EN ISO 14175