



CEWELD S3

TYPE	Solid drawn copper coated wire for the SAW process					
APPLICATIONS	Pipe work; offshore, pressure vessels, bridge, crane building, apparatus, and steam turbine construction.					
PROPRIÉTÉS	S3 is a Solid wire for CMn and mild steels with yield strength up to ~460 MPa Typical with FL 155 Flux.					
CLASSIFICATION	AWS	A 5.17: EH10K, A 5.23: EH10K				
	EN ISO	14171-A: S3				
	F-nr	6				
	FM	1				
CONVIENT POUR	Reh ≤ 460 MPa (67 ksi) ISO 15608: 1.2, 1.3, 2.1 1.5637, 1.6217, 1.6228, 1.0044-1.09821.0035 - 1.0570, 1.0345, 1.0425, 1.0481, 1.0308 - 1.0581, 1.0307 - 1.0582, 1.0440, 1.0472, 1.0475, 1.0416 to 1.0551 10Ni14, 12Ni14, 13MnNi6-3, 15NiMn6, S235JR-S355JR, S235JO-S355JO, S450JO, S235J2-S355J2, S275N-S460N, S275M-S460M, P235GH-P355GH, P275NL1-P460NL1, P215NL, P265NL, P355N, P285NH-P460NH, P195TR1-P265TR1, P195TR2-P265TR2, P195GH-P265GH, L245NB-L415NB, L450QB, L245MB-L450MB, GE200-GE240, A, B, D, E, A 32-E 36 ASTM A 106 Gr. A, B, C; A 181 Gr. 60, 70; A 283 Gr. A, C; A 285 Gr. A, B, C; A 350 Gr. LF1; A 414 Gr. A, B, C, D, E, F, G; A 501 Gr. B; A 513 Gr. 1018; A 516 Gr. 55, 60, 65, 70; A 573 Gr. 58, 65, 70; A 588 Gr. A, B; A 633 Gr. C, E; A 662 Gr. B; A 711 Gr. 1013; A 841 Gr. A; API 5 L Gr. B, X42, X52, X56, X60, X65 Domex 315-460MC,MC Plus, ML					
AGRÉMENTS	CE					
POSITIONS DE SOUDAGE	PAPBPC					
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL D'APPORT (%)	C	Si	Mn	P	S	
	0.1	0.1	1.5	0.015	0.015	
PROPRIÉTÉS MÉCANIQUES	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V	
					-40°C	-60°C
	As Welded	500	620	20	80	60
					Hardness	
					HRc	
ETUVAGE	Not required					
GAS ACC. EN ISO 14175						