



CEWELD AlMg 4.5Mn Tig

TYPE	Tig aluminium welding wire with high corrosion resistance					
TOEPASSINGEN	Filler metal for Magnesium and Manganese alloyed Aluminium with a maximum Magnesium content of 5%. This alloy shows very good mechanical properties that make it ideal for applications in shipyards, in car and railway industry and constructions of reservoirs and tanks.					
EIGENSCHAPPEN	Excellent weldability and good mechanical strength combined with good corrosion resistance against seawater are typical for this alloy. The weld deposit is free from porosity due to the special shaving process and cleaning method during production. AlMg4,5Mn is one of the highest grades within the range of aluminum alloys and covers a huge range of alloys. Thicker sections should be preheated (150°C) prior to welding.					
CLASSIFICATIE	AWS	A 5.10: ER5183				
	EN ISO	18273: S Al 5183 (AlMg4,5Mn0,7(A))				
	F-nr	22				
GESCHIKT VOOR	Aluminium alloys: AlMg4,5Mn, AlMg5, AlMg2Mn0,8, AlZnMg1, AlZnMgCu0,5, AlMgSi0,5, AlMgSi1, G-AlMg10, G-AlMg5, G-AlMg3Si, G-AlMg5Si, 3.3545, 3.3547, 3.3535, 3.3555, 3.3206, 3.3210, 3.2315, 3.3211, 3.4335, EN AW 5086, EN AW 5083, EN AW 5019, EN AW 5019, EN AW 6060, EN AW 6005A, EN AW 6082, EN AW 6061, EN AW 7020, EN AC 51300, EN AC 51400,					
GOEDKEURINGEN	CE					
LASPOSITIES						
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	Mn	Cr	Al	Mg		
	0.7	0.1	Rem.	4.5		
MECHANISCHE WAARDEN	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V	Hardness
	As Welded	140	300	18	RT	HRC
					30	
HERDROGEN	Not required					
GAS ACC. EN ISO 14175	I1, I3					