




CEWELD 347H Tig

TYPE	Solid Niobium stabilized stainless steel welding wire																	
TOEPASSINGEN	For welding stainless austenitic steels that are exposed to working temperatures up to 400°C.																	
EIGENSCHAPPEN	The weld deposit is scale-resistant up to approx. 800°C in normal atmosphere and oxidizing gases. The weld deposit is capable of taking a high polish. Structure: Austenite with delta ferrite																	
CLASSIFICATIE	AWS	A 5.9: ER347																
	EN ISO	14343-A: W 19 9 Nb																
	W.Nr.	~ 1.4551																
	F-nr	6																
	FM	5																
GESCHIKT VOOR	ISO 15608: 8.1 / TÜV Groupe 29 (+22+21) / E347, 19 9 Nb, 1.4551 1.4541, 1.4550, 1.4552 1.4319, 1.4306, 1.4306, 1.4301, 1.4303, 1.4308, 1.4310, 1.4312, (1.4000, 1.4001, 1.4002, 1.4003, 1.4006) X 6 NiTi 18 10, X 6CrNiNb 18 10, G-X 5CrNiNb 18 9, X 5CrNi 18 7, X 2CrNi 19 11, G-X 2CrNi 18 9, X 5CrNi 18 10, X 5CrNi 18 12 G-X, 6CrNi 18 9, X 12CrNi 17 7, G-X 10CrNi 18 8 AISI: 321, 347																	
GOEDKEURINGEN	CE																	
LASPOSITIES																		
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Ni</th> <th>Nb</th> </tr> </thead> <tbody> <tr> <td>0.04</td> <td>0.5</td> <td>1.9</td> <td>0.01</td> <td>0.01</td> <td>20</td> <td>10</td> <td>0.5</td> </tr> </tbody> </table>	C	Si	Mn	P	S	Cr	Ni	Nb	0.04	0.5	1.9	0.01	0.01	20	10	0.5	
C	Si	Mn	P	S	Cr	Ni	Nb											
0.04	0.5	1.9	0.01	0.01	20	10	0.5											
MECHANISCHE WAARDEN	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{P0.2} (MPa)</th> <th rowspan="2">R_m (MPa)</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th colspan="2">RT</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>390</td> <td>590</td> <td>31</td> <td colspan="2">80</td> <td>HRC</td> </tr> </tbody> </table>	Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness	RT		As Welded	390	590	31	80		HRC	
Heat Treatment	R _{P0.2} (MPa)					R _m (MPa)	A ₅ (%)		Impact Energy (J) ISO-V		Hardness							
		RT																
As Welded	390	590	31	80		HRC												
HERDROGEN	Not required																	
GAS ACC. EN ISO 14175	I1																	



CEWELD 347H Tig

347H TIG 1,6 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663413260