



CEWELD 310 Tig

TYPE	High heat resistant stainless steel welding wire for Tig welding.																				
TOEPASSINGEN	Common applications include industrial furnaces, annealing chambers, fused salt treatment installations and boiler parts, as well as heat exchangers.																				
EIGENSCHAPPEN	Solid drawn ,corrosion-resistant, chromium-nickel wire for welding heat-resistant austenitic steels of the 25% Cr, 20% Ni types. 310 has good general oxidation resistance, especially at high temperatures, due to its high Cr content. The alloy is fully austenitic and is therefore sensitive to hot cracking. The temperature limits for use under intermittent oxidation depend on cycle frequency. In no case shall a temperature of 1000°C be exceeded. This alloy can withstand relatively severe thermic shock, and is superior to type 309 L.																				
CLASSIFICATIE	AWS	A 5.9: ER310																			
	EN ISO	14343-A: W 25 20																			
	W.Nr.	1.4842																			
	F-nr	6																			
	FM	5																			
GESCHIKT VOOR	ISO 15608: 8.1 Austenitic ≤ 19 % Cr , TÜV 1000: Gr. 21-30, Type: 25% Cr, 22%Ni 1.4710, 1.4713, 1.4724, 1.4726, 1.4742, 1.4745, 1.4762, 1.4823, 1.4826, 1.4828, 1.4832, 1.4835, 1.4837, 1.4840, 1.4841, 1.4845, 1.4846, 1.4848, 1.4849, 253MA, X15CrNiSi 25 20, G-X40CrNiSi 25 12, G-X15CrNi 25 20, X8CrNi25-21 AISI 305, 310, 314 ASTM A297 HF / A297HJ																				
GOEDKEURINGEN	CE																				
LASPOSITIES																					
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>Cu</th> </tr> </thead> <tbody> <tr> <td>0.1</td> <td>0.5</td> <td>1.8</td> <td>0.01</td> <td>0.01</td> <td>26</td> <td>21</td> <td>0.3</td> <td>0.3</td> </tr> </tbody> </table>	C	Si	Mn	P	S	Cr	Ni	Mo	Cu	0.1	0.5	1.8	0.01	0.01	26	21	0.3	0.3		
C	Si	Mn	P	S	Cr	Ni	Mo	Cu													
0.1	0.5	1.8	0.01	0.01	26	21	0.3	0.3													
MECHANISCHE WAARDEN	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{P0,2} (MPa)</th> <th rowspan="2">R_m (MPa)</th> <th rowspan="2">A₅ (%)</th> <th colspan="3">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th>RT</th> <th>-196°C</th> <th>-40°C</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>405</td> <td>575</td> <td>45</td> <td>130</td> <td>45</td> <td>65</td> <td>HRc</td> </tr> </tbody> </table>	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V			Hardness	RT	-196°C	-40°C	As Welded	405	575	45	130	45	65	HRc	
Heat Treatment	R _{P0,2} (MPa)					R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V			Hardness										
		RT	-196°C	-40°C																	
As Welded	405	575	45	130	45	65	HRc														
HERDROGEN	Not required																				
GAS ACC. EN ISO 14175	I1																				



CEWELD 310 Tig

310 TIG 1,0 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663416124

310 TIG 1,6 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663416131

310 TIG 2,0 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663416148

310 TIG 2,4 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663416155

310 TIG 3,2 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663416162