



CEWELD ER 90 S-G (P92) Tig

TYPE	Medium alloyed, high-strength creep resistant 9% Chromium alloy.								
TOEPASSINGEN	TIG/GTAW wire for high temperature, creep resistant, modified 9%Cr1%Mo martensitic steel (T92/P92). Alloy T92/P92 is widely used in the power generating industry for fossil fuel ultra-super-critical (USC) power plant boilers and turbines; the alloy is also finding applications in the chemical and oil and gas industries.								
EIGENSCHAPPEN	T92/P92 steel is commonly used at service temperatures up to 620°C. V, Nb and N additions provide this 'creep strength enhanced ferritic' (CSEF) alloy with improved high temperature creep resistance compared to standard CrMo creep resistant alloys.								
CLASSIFICATIE	<table border="0"> <tr> <td>AWS</td> <td>A 5.28: ER 90S-G</td> </tr> <tr> <td>EN ISO</td> <td>21952-A: W ZCrMoWVNb 9 0,5 1,5</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>3</td> </tr> </table>	AWS	A 5.28: ER 90S-G	EN ISO	21952-A: W ZCrMoWVNb 9 0,5 1,5	F-nr	6	FM	3
AWS	A 5.28: ER 90S-G								
EN ISO	21952-A: W ZCrMoWVNb 9 0,5 1,5								
F-nr	6								
FM	3								
GESCHIKT VOOR	For matching P92, 9%Cr1.7%W0.5%Mo, creep resisting martensitic steels. X10CrWMoVNb 9 2 ASTM: A182 grade F92, A213 grade T92, A335 grade P92, A387 grade 92								

GOEDKEURINGEN CE

LASPOSITIES



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

C	Si	Mn	P	S	Cr	Ni	Mo	W	Nb
0.1	0.35	0.5	0.008	0.008	9.1	0.5	0.8	1.6	0.05

MECHANISCHE WAARDEN

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
730°C- 760°C 3h	550	630	17	HRc

HERDROGEN Not required

GAS ACC. EN ISO 14175 I1