

CEWELD NiFe 44Mn (NI-ROD)

TYPE	Solid Nickel-Iron-Manganese welding wire for cast iron.
TOEPASSINGEN	Ductile, gray and malleable Cast Iron and cast steel repairs, rebuilding wornout parts and also suitable for joining steel to cast Iron.
EIGENSCHAPPEN	Excellent wetting properties that enable this welding wire to weld with high welding speed due to the high manganese content. Thermal expansion is very low (close to NILO) and the weld deposit is extremely crack resistant.
CLASSIFICATIE	AWS EN ISO 1071: NiFeMn-CI
GESCHIKT VOOR	Grey cast iron, malleable, nodular : NF A 32-101 : FGL 150, 200, 250, 300, 350, 400. NF A 32-201 : FGS 370-17, 400-12, 500-7, 600-3, 700-2. NF A 32-702 : MN 350-10, 380-18, 450-6, 350-4, 650-3. DIN 1691 : CG-14, 18, 25, 30. DIN 1693 : GGG-40, 50, 60, 70. DIN 1692 : GTS-35, 45, 55, 65, 70.

GOEDKEURINGEN

LASPOSITIES



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)


Ni	Mn	Si	C	Fe
44	12	0.08	1.5	Rem.

MECHANISCHE WAARDEN

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded		690	35	190 HB

HERDROGEN Not required

GAS ACC. EN ISO 14175 I1, M21



CEWELD NiFe 44Mn (NI-ROD)

NIFE 44MN (NI-ROD) 1,2MM

Packaging	KG/unit	EanCode
BS-300	13,60	8720663420671