



CEWELD SG Ni3,5

TYPE	Solid MIG wire for extra low temperature applications.							
TOEPASSINGEN	Used in petrochemical industry where it finds applications in construction of cryogenic plant and associated pipework, in the manufacture, storage and distribution of volatile liquids and liquefied gases.							
EIGENSCHAPPEN	Excelent impact properties at subzero temperatures down to -80°C.							
CLASSIFICATIE	AWS	A 5.28: ER 80S-Ni3						
	EN ISO	14341-B: G 57P 7 M22 SN71						
	F-nr	6						
	FM	1						
GESCHIKT VOOR	ReH ≤ 550 MPa ISO 15608: 1.2 (275 < ReH < 360 MPa), 1.3 (ReH > 360 MPa < 550 MPa), 2.2 ReH > 460 MPa 1.0531,1.0984, 1.0986, 1.8900, 1.8901, 1.8902, 1.8903, 1.8904, 1.8905, 1.8907, 1.8910, 1.8912, 1.8915, 1.8917, 1.8926, 1.8930, 1.8932, 1.8935, 1.8937, 1.8986, 1.8970, 1.8971, 1.8972, 1.8973, 1.8975 11MnNi5-3, 13MnNi6-3, 12Ni14, S460N, S420N, S460NL, P460N, StE 420, StE 460, StE 500, StE 550 TStE 380, S420NL, P460NL1, P420NH, P460NH, TStE 420, TStE 460, TStE 500,TStE 550 WStE 380, WStE 420, WStE 460, WStE 500, WstE 550, StE 385.7, StE 385.7 TM, StE 415, L485ME ASTM A 203 Gr. D, E; A 350 Gr. LF1, LF2, LF3; A 420 Gr. WPL3, WPL6; A 516 Gr. 60, 65, 70; A 572 Gr. 42, 50, 55, 60, 65; A 633 Gr. A, D, E; A 662 Gr. A, B, C; A 707 Gr. L1, L2, L3; A 738 Gr. A; A 841 A, B, C; API 5 L X52, X60, X65, X52Q, X60Q, X65Q Oceanfit 52, Oceanfit 60, Oceanfit 65, Oceanfit 355, Oceanfit 420, Oceanfit 460, PAS 460-550, alform® 500 M, 550 M, aldur 500 Q, 500 QL, aldur 550 Q, 550 QL							
GOEDKEURINGEN	CE							
LASPOSITIES	      							
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	P	S	Ni	Cu	
	0.1	0.6	1	0.01	0.01	3.5	0.12	
MECHANISCHE WAARDEN	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V			Hardness
					-50°C	-60°C	-70°C	
	As Welded	570	640	24	95	60	45	HRC
HERDROGEN	Not required							
GAS ACC. EN ISO 14175								