


CEWELD SA 2209

TYPE	Stainless steel Duplex filler metal for submerged arc welding																		
TOEPASSINGEN	Boilers, tanks, vessels and similar objects that needs high strength and improved resistance against intergranular corrosion, pitting and stress corrosion.																		
EIGENSCHAPPEN	SA 2209 has high general corrosion resistance in media containing chloride and hydrogen sulfide. Combined with our fused flux FL 880 excellent results are obtained for both joining and cladding applications with self lifting slag and it leaves a fine rippled surface free from slag residues or pin holes. Also our agglomerated flux FL 838 can be used.																		
CLASSIFICATIE	<table border="0"> <tr> <td>AWS</td> <td>A 5.9: ER2209</td> </tr> <tr> <td>EN ISO</td> <td>14343-A: S 22 9 3 N L</td> </tr> <tr> <td>W.Nr.</td> <td>1.4462</td> </tr> <tr> <td>F-nr</td> <td>5</td> </tr> <tr> <td>FM</td> <td>6</td> </tr> </table>	AWS	A 5.9: ER2209	EN ISO	14343-A: S 22 9 3 N L	W.Nr.	1.4462	F-nr	5	FM	6								
AWS	A 5.9: ER2209																		
EN ISO	14343-A: S 22 9 3 N L																		
W.Nr.	1.4462																		
F-nr	5																		
FM	6																		
GESCHIKT VOOR	<p>ISO 15608: 10.1-10.2 Austenitic > 24 % Cr ≤ 4% Ni, DUPLEX 2209, 22%Cr 9%Ni 3%Mo 1.4417, 1.4462, 1.4362, 1.4162, 1.4463, 1.4460, 1.4583 X 2 CrNiMoSi 19 5, X 2 CrNiN 23 4, X 2 CrNiMoN 22 5 3, X10CrNiMoNb18-12 316LN, 318LN UNS S31803, S32205, S32304 SAF 2205 Fafer 4462, NKCr22, SM22Cr, Falc 223 UR 45N & UR 45N+, 2101, 2205, UR 35 N SAF 2304 mix 1.4462 X2CrNiMoN22-5-3 mit P235GH/ P265GH, S255N, P295GH, S355N, 16Mo3</p>																		
GOEDKEURINGEN	CE																		
LASPOSITIES																			
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>N</th> </tr> </thead> <tbody> <tr> <td>0.02</td> <td>0.8</td> <td>1.5</td> <td>0.02</td> <td>0.02</td> <td>22</td> <td>9</td> <td>3</td> <td>0.15</td> </tr> </tbody> </table>	C	Si	Mn	P	S	Cr	Ni	Mo	N	0.02	0.8	1.5	0.02	0.02	22	9	3	0.15
C	Si	Mn	P	S	Cr	Ni	Mo	N											
0.02	0.8	1.5	0.02	0.02	22	9	3	0.15											
MECHANISCHE WAARDEN	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{p0,2} (MPa)</th> <th rowspan="2">R_m (MPa)</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th>RT</th> <th>-60°C</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>570</td> <td>780</td> <td>25</td> <td>80</td> <td>40</td> <td>HRc</td> </tr> </tbody> </table>	Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness	RT	-60°C	As Welded	570	780	25	80	40	HRc		
Heat Treatment	R _{p0,2} (MPa)					R _m (MPa)	A ₅ (%)		Impact Energy (J) ISO-V		Hardness								
		RT	-60°C																
As Welded	570	780	25	80	40	HRc													
HERDROGEN	Not required																		
GAS ACC. EN ISO 14175																			



CEWELD SA 2209

SA 2209 2,4MM

Packaging	KG/unit	EanCode
K-415	25	8720663414601

SA 2209 3,2MM

Packaging	KG/unit	EanCode
K-415	25	8720663414243